



Conformance to standards:

Additional services to benefit you

PMA products conform to worldwide standards and regulations. As a pioneer in the field of cable protection, we have always given high priority to our own testing facilities, and we have consciously introduced stringent in-house standards. This approach has enabled PMA to exercise a significant influence on the development of international standards. Standards committees with responsibility for cable systems regularly ask our company to provide advice or participate as an active member.

符合标准

使您受益的附加服务

PMA 产品符合全球标准规则。作为电缆保护领域的先行者，**PMA** 一直优先发展自身的测试设备，并且有意识地引入了严格的内部测试标准。**PMA** 的这种措施对国际标准的发展起着非常重大的影响。负责电缆系统规则的标准委员会请求 **PMA** 提供建议或者以活跃成员的身份参与标准的制订。

High quality product from A-Z

From basic items to high-tech products, all of our products meet the most stringent quality requirements. Some of the outstanding are:

- resistance to temperature, weathering, UV radiation, and chemical agents
- high system pull-out resistance
- excellent fire protection characteristics (flammability, smoke density, and toxicity)
- excellent system ingress protection up to IP66, IP68 and IP69
- extremely long service life
- conformance to the EN ISO 9001:2015 quality standard

高质量产品：A-Z



PMA 所有产品，从基础产品到高科技产品，都满足最严格的质量要求。一些优异特性如下：

- 耐高温耐候，抗紫外线辐射，耐化学性。
- 优秀的抗拉伸性
- 极佳的防火特性（燃烧性能，烟雾，毒性）
- 极佳的防护等级达到 IP66, IP68 和 IP69
- 极长的工作寿命
- 符合 EN ISO 9001:2015 质量标准

IEC EN61386
PMA DO 9.21-4425

Resistance to fatigue during continuous bending

循环交变弯曲抗疲劳性测试




Both standards describe tests designed to evaluate conduit resistance to fatigue when exposed to continuous cycles of repetitive bending. The test procedure involves bending back and forth around a central pivotal point. Although the test procedure is the same for both standards there are differences in the test parameters and the classification of results. For a “pliable” classification according to IEC EN 61386 - 22 a conduit must withstand 3 cycles at the minimum declared operating temperature. For a “flexible” classification according to IEC EN 61386 - 23 a conduit must withstand 5000 cycles at the minimum declared operating temperature. PMA DO 9.21 - 4425 tests the conduit at 23°C and 50% r.h. but the test is not limited to a fixed number of cycles. It continues until the first signs of damage occur in order to find the actual performance limit.

这两项标准都描述了对于评估软管在循环交变弯曲中的抗疲劳性的测试。测试过程包括围绕中心枢轴点前后弯曲。尽管两种标准的测试程序相同，但测试参数和结果等级有所不同。根据标准 IEC EN 61386 - 22 中“可折弯”的定义表明，软管必须在已声明的最低工作温度下承受最少 3 次循环测试。根据标准 IEC EN 61386 - 23 中“柔软性”的定义表明，软管必须在已声明的最低工作温度下承受 5000 次循环测试。根据 PMA DO 9.21 - 4425 标准，软管在 23°C/50% 相对湿度环境下测试，软管测试不限固定的循环次数，直到软管破裂为止，以便找到实际的性能极限。

PMA DO 9.21-4420

Resistance to fatigue during continuous bending

循环交变弯曲抗疲劳性测试





This PMA internal standard describes a demanding test for conduit fatigue when exposed to continuous repetitive bending. The conduit is fixed at the top of the apparatus, it passes over and under two pulley wheels. A weight is suspended at the bottom end simulating the weight of cables within the conduit. The pulley wheels move up and down continuously bending the conduit twice through 180° over its entire length. The test is performed at 23°C and 50% r.h. and continues until the first signs of damage occur.

根据 PMA 标准描述，软管需经受苛刻的连续性重复的弯曲测试，以评估软管的抗疲劳性。软管一端固定于设备顶部，另一端从两个滑轮上下依次穿过，并于底部悬挂一重物，模拟软管内电缆重量，此时软管弯曲幅度达到 180°，并两次连续弯曲，滑轮开始沿整个软管长度连续上下移动。测试在 23°C/50% 相对湿度环境下进行，并持续到出现第一个破裂为止。

IEC EN61386
PMA DO 9.21-4430

Flammability tests

阻燃性能测试




PMA DO 9.21 - 4430 evaluates flammability characteristics using a defined flame from a standard burner. The time before ignition, fire propagation behaviour and extinguishing time after removal of the heat source are all factors in evaluating the flammability of conduits for a self-extinguishing classification. IEC 61386 uses the EN 60695-2-10 glow wire test procedure to evaluate the flame propagation behaviour of conduits allocating the classifications. Non-flame propagating or flame propagating.

PMA DO9.21-4430 使用标准燃烧器特定的火焰来评估阻燃性能。被燃着前的时间、火焰传播、移去火焰后的自熄时间等，都是评估软管自熄灭等级的因素。IEC 61386 使用 EN 60695-2-10 灼热丝测试来评估软管的火焰传播行为的等级。非火焰传播或火焰传播。

IEC EN61386
PMA DO 9.21-4320

Compression strength test

抗压强度测试



Both standards describe a test designed to evaluate conduit resistance to compression forces. Excessive deformation of a conduit under compression could potentially cause damage to cables being protected within it.

The force required to compress the conduit between two square plates to a specific % of its original diameter is measured. Relaxation over time and recovery after removal of the force are evaluated.

The tests are performed at 23°C and 50% r.h.

IEC EN 61386 uses two 50mm x 50mm plates and allows 25% deformation.

PMA DO 9.21 - 4320 records results with 50mm x 50mm and 100mm x 100mm test plates and allows 20% deformation.

这两项标准都描述了评估软管抗压强度的测试。软管在压力状态下严重变形可能会对其内受保护的电缆造成损坏。

测试将软管放在两块四方形板之间进行挤压，压缩至其原始直径的特定百分比所需的力。评估移除压力后，随着时间舒张和复原状态。

测试在 23°C/50%相对湿度的环境下进行。



IEC EN 61386 标准，是使用两块 50 mm x 50 mm 的板测试，允许 25% 的变形。

PMA DO 9.21 - 4320 标准，记录使用 50 mm x 50 mm 和 100 mm x 100 mm 的板测试，但只允许 20% 的变形。

IEC EN61386
PMA DO 9.21-4610

System pull-out test

系统拉伸强度测试



Both standards are designed to test the security of the conduit to fitting connection.

Two fittings with a piece of conduit between them are pulled apart with steadily increasing force. Extension of the conduit is recorded graphically against the force applied. The force required to pull the conduit out of the fitting is determined.

The tests are performed at 23°C and 50% r.h.

这两项标准是评估软管与管接头连接的安全性。


"两个管接头之间连接一段软管，随着力的不断增加而被拉开。以图形方式记录软管的拉伸情况。以确定将软管拉出管接头所需的力。"

测试在 23°C/50%相对湿度环境下进行。

IEC EN61386
PMA DO 9.21-4330

Resistance to impact test

抗冲击测试



These standards describe tests to evaluate the resistance of conduits to high energy impacts.

They can be performed on conduits at various temperatures.

Weights of different mass are dropped from an adjustable height directly onto a conduit sample which has been conditioned at the specified temperature. The energy of impact can be calculated as mass X gravity X height. The geometry of the object falling onto the conduit is regulated.

No breaks, cracks or excessive permanent deformation should be visible after the test.


这些标准都描述了评估软管抗冲击强度的测试。

它们需要在不同温度下在软管上进行。不同重量的砝码从可调的高度直接落在指定温度下调节的软管样品上。撞击能量可以计算为：重量 X 地心引力 X 高度。落在软管上的物体形状已规定。测试后不应出现断裂、裂纹或严重持久性变形。

PMA DO 9.21-4380

Flexibility at low temperature

低温下柔韧性



This standard describes a test procedure to evaluate the flexibility of conduits at low temperatures.

The conduit under test is placed in a climatic chamber at the lowest specified operating temperature for four hours.

It is then removed and immediately bent around a mandrel of diameter related to the outside diameter (OD) of the conduit.

Four classifications are achievable based upon the smallest achievable bending radius without damage.

本标准是评估在低温下的软管柔韧性测试。将软管放置在特定最低工作温度下的控制箱内4个小时。


然后将其取出，并立即绕着直径约等于软管外径（OD）的芯棒弯曲。

在基于在最小可达到的弯曲半径和无损伤的情况下，分四种等级评估。

PMA DO 9.21-4360

Thermal ageing test

高温老化测试



This standard describes a procedure designed to evaluate the thermal stability of a conduit and its resistance to thermal ageing.

The conduit is exposed to a temperature significantly above the maximum recommended continuous operating temperature for 168 hours, 160°C (PA6) or 150°C (PA12).

The flexibility at low temperature procedure DO 9.21-4380 is performed both before and after the thermal ageing procedure as an indicator of change to material characteristics.

本标准是评估软管高温稳定性及其耐高温老化性的测试。

将软管放置明显地高于其最高推荐的连续工作温度的控制箱内长达168小时，160°C（PA6）或150°C（PA12）

根据DO 9.21-4380标准，软管在高温老化过程的前和后根据在低温下柔韧性测试方法作比较，以作为材料特性变化的指标。



PMA products offer complete protection!

PMA 产品提供完全保护！

Ingress protection (IP) according to IEC EN60529

Ingress Protection (IP)

= A standard to classify product performance regarding ingress protection.

Different number = different protection!

For example, product classified as IP x8 are not automatically protected against jet water! Immersion tests for classifications IPx7 and IPx8 differ from the tests for protection against jet water for IPx9, IPx6, IPx5, or IPx4.

Therefore PMA cable protection systems are tested regarding different sealing requirements.

根据国际标准 IEC EN60529 IP 防护等级

防止进入 (IP)

= 划分产品防护等级的标准

不同的数字 = 不同的防护

比如：防护等级 IPx8 的产品并不能自动的代表对喷射的水提供防护。浸水测试划分 IPx7, IPx8 等级，而喷水防护测试用来划分 IPx9, IPx6, IPx5, IPx4 等级。

因此：**PMA 电缆保护系统是根据不同的密封要求做相应测试的。**

PMA products

PMA 产品

PMAFIX Pro
IP68 / IP69

PMAFIX
IP68 + WPS

PMAFIX
IP68 / IP68GT

PMAFIX
IP66

SMART-LINE
IP66

Icon	IP Rating	Description	PMAFIX Pro IP68 / IP69	PMAFIX IP68 + WPS	PMAFIX IP68 / IP68GT	PMAFIX IP66	SMART-LINE IP66
	IPx4	Splash water from all directions 各个方向飞溅的水	✓	✓	✓	✓	✓
	IPx5	Jet water at any angle 任一角度喷射的水	✓	✓	✓	✓	✓
	IPx6	Powerful jet water from any angle 任一角度强喷射的水	✓	✓	✓	✓	✓
	IPx7	Submersion (1m, 30 min.) 浸没 (1米, 30分)	✓	✓	✓		
	IPx8	Submersion at time and / or pressure > IP x 7 浸没的时间和/或压力大于 IP x 7	✓	✓	✓		
	IPx9	High pressure and temperature (up to 80 bar) water from any angle 任一角度高达 80 巴的高压和高温喷水	✓	✓*	✓*	✓*	✓*

* IEC EN60529 can be fulfilled without WPS (Water impact protection ring). PMA recommends the use of WPS ring for trouble free practical applications.
没有 WPS (抵抗水冲击的保护环), 也可符合 IEC EN60529。但 PMA 推荐使用 WPS 避免实际应用时出现问题。

Ingress protections IEC EN 60529

Dust 尘埃

Protection against contact and penetration of foreign objects

Degree of protection (contact / foreign bodies)

对接触和外来物质穿透的防护

防护等级代号（接触 / 外界物体）

IP 6 8

	0	No protection. 无防护。
	1	Objects greater than 50mm Ø, accidental touch by hands. 防止人体（如手掌）因意外而接触到电器内部的零件，防止较大尺寸（直径大于50mm）的外物侵入。
	2	Objects greater than 12.5mm accidental touch by fingers Ø. 防止人的手指接触到电器内部的零件，防止中等尺寸（直径大于12.5mm）的外物侵入。
	3	Objects greater than 2.5mm Ø, e.g. tools/wires. 防止直径或厚度大于2.5mm的工具、电线及类似的小型外物侵入而接触到电器内部的零件。
	4	Objects greater than 1mm Ø, e.g. tools/wires. 防止直径或厚度大于1.0mm的工具、电线及类似的小型外物侵入而接触到电器内部的零件。
	5	Protected against dust - limited ingress (no harmful deposits). 防护灰尘。不可能完全阻止灰尘进入，但灰尘进入的数量不会影响设备的正常运行。
	6	Totally protected against dust (dust-tight). 完全防止外物及灰尘侵入。



防护等级根据 IEC EN 60529

Water 水











Protection against fluids

Degree of protection (water)

防护液体

防护等级代号（水）

IP 6 8

	0	No protection. 无防护。
	1	Protected against vertically falling drops of water. 防护水滴，垂直落下的水滴。
	2	Protected against direct sprays of water 15° from vertical. 防护从垂直方向倾斜15度喷洒的水。
	3	Protected against sprays of water to 60° from vertical. 防护从垂直方向倾斜60度喷洒的水。
	4	Protected against water sprayed from all directions - limited ingress permitted. 防止各个方向飞溅或喷洒而来的水 - 有限度的水进入是允许的，但不会对设备造成损坏。
	5	Protected against low pressure jets of water from all directions - limited ingress permitted. 防止持续至少3分钟的低压喷水 - 有限度的水进入是允许的，但不会对设备造成损坏。
	6	Protected against strong pressure jets of water, heavy seas - limited ingress permitted. 防止大浪或持续至少3分钟的高压喷水 - 有限度的水进入是允许的，但不会对设备造成损坏。
	7	Protection against the effects of immersion between 15cm - 1m, 30 minutes. 防止浸水时水的进入，在深达15厘米至1米的水中，30分钟的浸泡影响。
	8	Protection against long periods of immersion under a quoted pressure, to be discussed between the manufacturer and the user. 防止在特定压力下较长时间沉没时水的进入，准确的条件由制造商和用户商讨。
	9	Protection against high temperature (80°C) & extremely high pressure stream water jet. 防止极高喷射水压的高温（80°C）水的进入。


Thread dimensions

螺纹尺寸

IEC EN 60423

Metric fine thread

公制细螺纹




Metric	Pitch 螺距	Major \varnothing 主外径 D1	Major \varnothing 辅外径 D2	Hole 孔 -0 / + 0.3
	mm	mm	mm	mm
12	1.5	12	10.16	12.0
16	1.5	16	14.16	16.0
20	1.5	20	18.16	20.0
25	1.5	25	23.16	25.0
32	1.5	32	30.16	32.0
40	1.5	40	38.16	40.0
50	1.5	50	48.16	50.0
63	1.5	63	61.16	63.0

DIN 40430

PG thread

PG 螺纹



PG	Pitch 螺距	Major \varnothing 主外径 D1	Major \varnothing 辅外径 D2	Hole 孔
	mm	mm	mm	mm
07	1.270	12.5	11.28	12.7
09	1.411	15.2	13.86	15.4
11	1.411	18.6	17.26	18.8
13.5	1.411	20.4	19.06	20.7
16	1.411	22.5	21.16	22.8
21	1.588	28.3	26.78	28.6
29	1.588	37.0	35.48	37.4
36	1.588	47.0	45.48	47.5
48	1.588	59.3	57.78	59.8


Thread dimensions

螺纹尺寸

DIN 259 Bl. 3
ISO 228100 / 1

Gas pipe thread

Gas 螺纹




GAS	Pitch 螺距	Major \varnothing 主外径 D1	Major \varnothing 辅外径 D2	Hole 孔
	mm	mm	mm	mm
1/4"	1.337	13.157	11.445	13.4
3/8"	1.337	16.662	14.950	17.0
1/2"	1.814	20.955	18.631	21.3
3/4"	1.814	26.441	24.117	26.8
1"	2.309	33.249	30.291	33.7
1 1/4"	2.309	41.910	38.952	42.4
1 1/2"	2.309	47.803	44.845	48.31
2"	2.309	59.614	56.656	60.2


ANSI / ASME B1.20

American standard
taper pipe thread

美国标准锥管螺纹




NPT	Pitch 螺距	Major \varnothing 主外径 D1	Hole 孔 D2
	mm	mm	mm
1/4"	1.411	13.716	13.9
3/8"	1.411	17.145	17.4
1/2"	1.814	21.336	21.6
3/4"	1.814	26.670	26.9
1"	2.209	33.401	33.7
1 1/4"	2.209	42.164	42.4
1 1/2"	2.209	48.260	48.5
2"	2.209	60.325	60.6



Insertion depth for PMA conduits into corresponding PMAFIX connectors

PMA 软管与对应的 PMAFIX 管接头在安装过程中的插入深度



Insertion depth for PMA conduits into corresponding PMAFIX Pro connectors

PMA 软管与对应的 PMAFIX Pro 管接头在安装过程中的插入深度

The dimensions given below have to be taken into account when calculating the length of conduit necessary between two connectors.

The insertion depth should be taken into account for each connector as mentioned below.


在两个管接头之间计算软管长度时，以下尺寸必须要计算在内。

在每个管接头内的插入深度要额外计算，请参照下表。

Nominal width, conduit 软管标称内径	PMAFIX insertion depth (EV nominal) PMAFIX 插入深度 (EV)	PMAFIX Pro insertion depth (EH nominal) PMAFIX Pro 插入深度 (EH)
NW	mm	mm
07	22	-
10	24	28.5
12	27	34.0
17	35	39.0
23	37	41.5
29	37	47.0
36	51	51.5
48	51	57.5


If wrongly installed, corresponding IP class may not be achieved.

如不正确安装，将不能达到指定的IP防水防尘等级。



Inside diameter of metric threads to inside diameter of conduits
公制螺纹内径与软管内径

Conduit 软管			Connector with metric thread 公制螺纹管接头		
Nominal width NW 标称内径			Inside diameter mm (nom.) ID内径 (毫米)		
Standard 标准	Metric 公制	Inside \varnothing nominal (mm) 正常内径 (毫米)	Thread size 螺纹尺寸	Metal thread 金属螺纹	Polyamide thread 聚酰胺螺纹
07	10	6.2	M12	-	8.0
10	12	9.6	M12	5.7	8.0
10	12	9.6	M16	9.6	11.0
12	16	12.0	M16	9.7	11.0
10	12	9.6	M20	-	13.0
12	16	12.0	M20	13.5	13.0
17	20	16.2	M20	13.5	14.6
23	25	22.6	M20	-	15.0
17	20	16.2	M25	18.3	19.0
23	25	22.6	M25	18.4	19.0
23	25	22.6	M32	24.2	24.0
29	32	29.0	M32	25.4	26.0
29	32	29.0	M40	31.4	32.0
36	40	36.5	M40	32.6	32.0
36	40	36.5	M50	39.5	39.0
48	50	47.5	M50	41.5	42.0
48	50	47.5	M63	51.4	53.0



Inside diameter of PG threads to inside diameter of conduits
PG 螺纹内径与软管内径

Conduit 软管			Connector with PG thread PG 螺纹管接头		
Nominal width NW 标称内径			Inside diameter mm (nom.) ID内径 (毫米)		
Standard 标准	Metric 公制	Inside \varnothing nominal (mm) 正常内径 (毫米)	Thread size 螺纹尺寸	Metal thread 金属螺纹	Polyamide thread 聚酰胺螺纹
07	10	6.2	PG07	-	8.0
10	12	9.6	PG09	9.5	10.0
12	16	12.0	PG11	12.5	13.0
-	-	-	PG13.5	14.5	14.5
17	20	16.2	PG16	16.5	17.5
23	25	22.6	PG21	22.0	22.5
29	32	29.0	PG29	30.0	30.5
36	40	36.5	PG36	40.0	37.5
-	-	-	PG42	-	46.0
48	50	47.5	PG48	49.5	50.0

Recommended torques for PMA connectors

PMA 管接头螺纹推荐扭矩

Tightening torques for PMA polyamide thread connectors to threaded holes or with lock nuts
适用于PMA聚酰胺螺纹管接头连接至螺纹孔或锁紧螺母的拧紧扭矩



Metric polyamide thread size 公制, 聚酰胺螺纹尺寸	Torque 扭矩 (Nm)	NPT polyamide thread size NPT制, 聚酰胺螺纹尺寸	Torque 扭矩 (Nm)
M12	1.5	NPT 1/2"	4.0
M16	3.0	NPT 3/4"	6.0
M20	4.0	NPT 1"	8.0
M25	6.0	NPT 1 1/4"	9.0
M32	8.0	NPT 1 1/2"	15.0
M40	9.0	NPT 2"	15.0
M50	10.0		
M63	10.0		



PG polyamide thread size PG制, 聚酰胺螺纹尺寸	Torque 扭矩 (Nm)
PG07	1.5
PG09	1.5
PG11	2.0
PG13.5	2.5
PG16	4.0
PG21	5.0
PG29	9.0
PG36	15.0
PG48	15.0



UNEF polyamide thread size UNEF, 聚酰胺螺纹尺寸	Torque 扭矩 (Nm)
1/2"-28 UNEF	2.0
9/16"-24 UNEF	3.0
5/8"-24 UNEF	3.0
11/16"-24 UNEF	3.0
3/4"-20 UNEF	4.0
13/16"-20 UNEF	4.0
7/8"-20 UNEF	8.0
15/16"-20 UNEF	8.0
1"-20 UNEF	8.0
1 1/16"-18 UNEF	10.0
1 3/16"-18 UNEF	10.0
1 1/4"-18 UNEF	10.0
1 5/16"-18 UNEF	10.0
1 3/8"-18 UNEF	10.0
1 7/16"-18 UNEF	15.0
1 5/8"-18 UNEF	15.0
1 3/4"-18 UNS	15.0
2"-18 UNS	15.0

Please note:
请注意:

These recommendations are guidelines. Please take into account the influence of the mating thread during assembly.
这些建议仅作为指导方针。组装过程中请考虑与其适配螺纹的影响。

These values are based on measurements under standard climatic conditions (23°C / 50% relative humidity).
这些数据来源于标准环境下测量 (23°C / 50% 相对湿度)。

Recommended torques for PMA connectors PMA 管接头螺纹推荐扭矩

Tightening torques for PMA metal thread connectors to threaded holes or with lock nuts
适用于PMA金属螺纹管接头连接至螺纹孔或锁紧螺母的拧紧扭矩



Metric metal thread size 公制, 金属螺纹尺寸	Torque 扭矩 (Nm)	NPT metal thread size NPT制, 金属螺纹尺寸	Torque 扭矩 (Nm)
M12	4.0	NPT 1/2"	6.0
M16	4.0	NPT 3/4"	8.0
M20	6.0	NPT 1"	10.0
M25	8.0	NPT 1 1/4"	15.0
M32	10.0	NPT 1 1/2"	15.0
M40	15.0	NPT 2"	15.0
M50	15.0		
M63	15.0		



PG metal thread size PG制, 金属螺纹尺寸	Torque 扭矩 (Nm)
PG07	3.5
PG09	4.0
PG11	6.0
PG13.5	6.0
PG16	7.0
PG21	8.0
PG29	10.0
PG36	15.0
PG48	15.0



UNEF metal thread size UNEF, 金属螺纹尺寸	Torque 扭矩 (Nm)
1/2"-28 UNEF	4.0
9/16"-24 UNEF	5.0
5/8"-24 UNEF	5.0
11/16"-24 UNEF	5.0
3/4"-20 UNEF	6.0
13/16"-20 UNEF	6.0
7/8"-20 UNEF	10.0
15/16"-20 UNEF	10.0
1"-20 UNEF	10.0
1 1/16"-18 UNEF	10.0
1 3/16"-18 UNEF	10.0
1 1/4"-18 UNEF	10.0
1 5/16"-18 UNEF	10.0
1 3/8"-18 UNEF	10.0
1 7/16"-18 UNEF	15.0
1 5/8"-18 UNEF	15.0
1 3/4"-18 UNS	15.0
2"-18 UNS	15.0
2 1/4"-16 UN	15.0

Please note:
 请注意:

These recommendations are guidelines. Please take into account the influence of the mating thread during assembly.
 这些建议仅作为指导方针。组装过程中请考虑与其适配螺纹的影响。

These values are based on measurements under standard climatic conditions (23°C / 50% relative humidity).
 这些数据来源于标准环境下测量 (23°C / 50% 相对湿度)。

Recommended torques for PMA connectors

PMA 管接头螺纹推荐扭矩

Tightening torques for fixation screws for PMA conduit clamps, PMA conduit supports or PMA flange
PMA管夹、PMA软管固定夹或PMA法兰上的固定螺钉拧紧扭矩

Thread size 螺纹尺寸	Torque 扭矩 (Nm)
M4	2.0
M5	3.0
M6	4.0
M8	10.0
M10	15.0

Maximum recommended tightening torques for PMA strain relief connectors with Pflitsch UNI Dicht elements
适用于带有Pflitsch UNI Dicht元件的PMA消除应力管接头的最大推荐拧紧扭矩



The tightening torque values quoted below for PMA fittings with Pflitsch UNI Dicht strain relief elements are absolute maximum values. Torque values should be adjusted for the type of cable and sealing insert in use but should not exceed the listed values. Please ensure correct size tooling is used to apply the tightening torque to avoid damage to the fitting body.

These values apply for:

- The strain relief element compression thread
- The termination thread
- Lock nuts attached to the termination thread

下面引用的带有Pflitsch UNI Dicht消除应力元件的PMA管接头的拧紧扭矩值为绝对最大值。

扭矩值应根据使用的电缆和密封插入件的类型进行调整，但不应超过所列值。

请确保使用正确尺寸的工具来施加拧紧扭矩，以免损坏管接头。

这些值适用于：

- 消除应力元件的压紧螺纹
- 管接头端接螺纹
- 连接到端接螺纹的锁紧螺母

Thread size 螺纹尺寸	Metal 金属 NVNZ-MxxxS/Px, NVEZ-MxxxV/P NKNZ-Mxxx/Px, NKEZ-Mxxx/Px [IEC EN 62444] [Nm]	Thread size 螺纹尺寸	Metal 金属 NVNZ-PxxxS/Px [IEC EN 62444] [Nm]
M12	6.0	PG07	6.0
M16	8.0	PG09	8.0
M20	10.0	PG11	10.0
M25	10.0	PG13.5	10.0
M32	15.0	PG16	10.0
M40	20.0	PG21	15.0
M50 (Clamping range 27-32, 29-34) 夹紧范围 27-32, 29-34	30.0	PG29	20.0
M50 (Clamping range 32-36, 36-40) 夹紧范围 32-36, 36-40	35.0	PG36	30.0
M63	40.0	PG48	40.0

The following values apply for PMA fittings with metric / PG termination thread and correspond to the Pflitsch recommended tightening torques for UNI Dicht cable glands with metric termination thread.

以上值适用于具有公制 / PG 端接螺纹的 PMA 管接头，并对应于 Pflitsch 推荐的具有公制端接螺纹的 UNI Dicht 电缆索头的拧紧扭矩。

Manufacturer's data for tightening torques of UNI Dicht cable glands with metric & PG connecting thread for feedthroughs with internal threads and for through holes with locknuts.

生产商提供的数据适用于拧紧带公制或 PG 制螺纹的 UNI Dicht 电缆索头，在带内螺纹的穿孔和带锁紧螺母的通孔上所需的扭矩。

Please note 请注意

Table figures are general terms of reference. The torque depends on the cable used and the insert sealing; it should not, however, exceed the figures stated in the table.

表格中的数值是通用的参考值。扭矩取决于使用的电缆和密封插入件；但是，不应超出表中列出的数值。

Recommended torques for PMA connectors



PMA 管接头螺纹推荐扭矩

Maximum recommended tightening torques for PMA strain relief connectors with Jacob PERFECT elements
适用于带 Jacob PERFECT 插入件的 PMA 消除应力管接头的最大推荐拧紧扭矩



Metric 公制

Thread size 螺纹尺寸	Metal 金属 NVNZ - MxxxS - xx / NVEZ - MxxxV - xx NKNZ - MxxxS - xx / NKEZ - Mxxx - xx [Nm]	Thread size 螺纹尺寸	Polyamide 聚酰胺 S / BVNZ - MxxxS [Nm]
	Necessary to fulfill IEC EN 62444 必须满足 IEC EN 62444 标准		Necessary to fulfill IEC EN 62444 必须满足 IEC EN 62444 标准
M12	3.5	M12	1.5
M16	3.5	M16	2.5
M20	3.5	M20	3.5
M25	6.7	M25	5.0
M32	12.0	M32	5.0
M40	13.5	M40	7.5
M50	16.0	M50	7.5
M63	15.0	M63	13.0

PG PG制

Thread size 螺纹尺寸	Metal 金属 NVNZ - PxxxS / NVEZ - PxxxV [Nm]	Thread size 螺纹尺寸	Polyamide 聚酰胺 S / BVNZ - PxxxS [Nm]
PG07	6.25	PG07	2.5
PG09	6.25	PG09	3.75
PG11	6.25	PG11	3.75
PG13.5	6.25	PG13.5	3.75
PG16	7.5	PG16	5.0
PG21	10.0	PG21	7.5
PG29	10.0	PG29	7.5
PG36	10.0	PG36	7.5
PG48	10.0	PG48	7.5






The manufacturer of the PERFECT strain relief insert recommends the use of the tightening torques quoted in VDE 0619 both for fixing cable glands to metal plates, threaded holes and for the compression of the strain relief part.

根据德国 VDE 0619 标准, PERFECT 消除应力插入件的生产商推荐使用的拧紧扭矩适用于固定电缆索头在金属板通孔, 螺纹孔和消除应力部件的压紧组件。

Recommended torques for PMA connectors

PMA 管接头螺纹推荐扭矩

Tightening torques for PMA purely metallic connectors and adapters (e.g. SCA, SWA, MAVI, MONK, JENQ, NSNV, NSBIV)
适用于PMA纯金属管接头和适配器的拧紧扭矩 (如 SCA, SWA, MAVI, MONK, JENQ, NSNV, NSBIV系列)

	Thread size	Torque	Thread size	Torque	Thread size	Torque
	螺纹尺寸	扭矩 (Nm)	螺纹尺寸	扭矩 (Nm)	螺纹尺寸	扭矩 (Nm)
	M16	10.0	NPT 1/2"	15.0	PG09	15.0
	M20	20.0	NPT 3/4"	20.0	PG11	15.0
	M25	30.0	NPT 1"	30.0	PG13.5	20.0
	M32	35.0	NPT 1 1/4"	35.0	PG16	30.0
	M40	35.0	NPT 1 1/2"	40.0	PG21	30.0
	M50	40.0	NPT 2"	40.0	PG29	35.0
	M63	40.0			PG36	40.0
					PG48	40.0

Tightening torques for PMA divisible lock nuts with PMA divisible connectors
适用于PMA可分螺母和可分管接头的拧紧扭矩

Tightening torques for PMA divisible lock nuts with PMAFIX polyamide thread connectors
适用于PMA可分螺母和PMAFIX管接头的拧紧扭矩

Thread size	Torque	Thread size	Torque
螺纹尺寸	扭矩 (Nm)	螺纹尺寸	扭矩 (Nm)
M16	tighten by hand 用手拧紧	M16	tighten by hand 用手拧紧
M20	tighten by hand 用手拧紧	M20	3.0
M25	4.0	M25	4.0
M32	6.0	M32	6.0
M40	8.0	M40	8.0
M50	10.0	M50	10.0



Please note 请注意

These recommendations are guidelines. Please take into account the influence of the mating thread during assembly.
这些建议仅作为指导方针。组装过程中请考虑与其适配螺纹的影响。

These values are based on measurements under standard climatic conditions (7 days, 23°C / 50% relative humidity).
这些数据来源于标准环境下测量 (7天, 23°C / 50% 相对湿度)。

Reference list for O-rings to metal threads

适配于金属螺纹的O型圈列表

Model of connector 管接头型号	Thread size 螺纹尺寸	O-ring ID x d O型圈 内径 x 厚度	Order no. 订货号
1. NVNV-Mxxx-x. 2. NVAV-Mxxx-x. 3. NVBV-Mxxx-x. 4. NVWV-Mxxx-x. 5. NSBV-Mxxx-x. 6. NSWV-Mxxx-x. 7. NSNV-Mxxx-x. 8. NKNH-Mxxx-x. 9. NKAH-Mxxx-x. 10. NKBH-Mxxx-x. 11. BVEMV-Mxxx-x. 12. BVEMV-MxxxSW-x. 13. SCA-Mxx. 14. SCAK-Mxx-xx. 15. SWA-Mxx-xx. 16. MAVI-Mxx / xx. 17. MAVIK-Mxx / xx.	M12 x 1.5	9 x 2.0	OR9.00 x 2.00
	M16 x 1.5	13 x 2.0	OR13.00 x 2.00
	M20 x 1.5	17 x 2.0	OR17.00 x 2.00
	M25 x 1.5	22 x 2.0	OR22.00 x 2.00
	M32 x 1.5	29 x 2.0	OR29.00 x 2.00
	M40 x 1.5	36 x 2.0	OR36.00 x 2.00
	M50 x 1.5	47 x 2.0	OR47.00 x 2.00
	M63 x 1.5	60 x 2.0	OR60.00 x 2.00

Model of connector 管接头型号	Thread size 螺纹尺寸	O-ring ID x d O型圈 内径 x 厚度	Order no. 订货号
1. NVNV-Pxxx. 2. NVAV-Pxxx. 3. NVBV-Pxxx. 4. NVWV-Pxxx. 5. NSBV-Pxxx-x. 6. BVEMV-Pxxx. 7. BVEMV-Pxxx-133. 8. SCA-Pxx. 9. SWA-Pxx. 10. MAVI-Pxx / xx.	PG 07	10 x 1.5	OR10.00 x 1.50
	PG 09	13 x 1.5	OR13.00 x 1.50
	PG 11	16 x 1.5	OR16.00 x 1.50
	PG 13.5	18 x 1.5	OR18.00 x 1.50
	PG 16	20 x 1.5	OR20.00 x 1.50
	PG 21	24 x 1.5	OR24.00 x 1.50
	PG 29	33 x 2.0	OR33.00 x 2.00
	PG 36	42 x 2.0	OR42.00 x 2.00
	PG 42	51 x 2.0	OR51.00 x 2.00
	PG 48	54 x 2.5	OR54.00 x 2.50

Life expectancy of PMA's sealings NVN3, O-rings (OR) and SVN4 PMA 密封系列产品 NVN3、OR 和 SVN4 的使用寿命

PMA is recognized as worldwide market leader for high reliability polyamide cable protection systems for various applications in the rail industry. Our PMAFIX IP68 connectors have been used extensively for static, dynamic, internal and external applications, under carriages, on bogies and on the roof exposed to high levels of UV radiation and extreme weather conditions for up to 30 years now.

PMA一直被公认为全球市场领导者，具有高可靠性的聚酰胺电缆保护系统，适用于铁路行业的各种应用需求。我们的PMAFIX IP68管接头已经广泛应用于静态、动态、内部和外部，且在车厢、转向架和车顶暴露在高紫外线辐射和极端天气条件下其使用寿命已经长达30年。

The NVN3, OR and SVN4 sealing types are integral parts of the PMAFIX IP68 connectors series. The used high-performance materials are responsible for creating an efficient, long term seal. PMA has received no reports of insufficient product lifetime in installations where the recommended installation methods have been followed closely and the products have been operated within their specification. Although thin-walled sealing elements made of elastomeric materials are more sensitive than the more robust connectors and conduits, their expected lifetime can be up to 20 years. It is advised to plan a preventive maintenance check after 10 years installation.

NVN3密封帽、OR O型圈和SVN4扁平垫圈密封系列是PMAFIX IP68系列管接头中不可缺少的部分。其使用的高性能材料可有助于提供高效，长期的密封效果。在安装中，产品将严格遵循推荐的安装方法，并且产品已经在其规范内操作，目前为止PMA未收到关于在安装中产品减少寿命的报告。虽然由弹性材料制成的薄壁密封元件比更结实的管接头和软管更加敏感，但它们的预期寿命可长达20年。建议在安装10年后进行预防性维修检查。

Factors which may negatively affect the lifetime of NVN3, OR and SVN4 are as follows.

可能对NVN3、OR和SVN4使用寿命减少的因素有如下几方面。

- Heat exposure. 暴露于高温。
- Exposure to aggressive chemicals, please refer to PMA chemical resistance data.
接触到腐蚀性化学品，请参考PMA耐化学腐蚀数据表。
- Mechanical stress caused by movement of the conduit within the connector leading to wear. This should be avoided by preventing torsion forces in the application, possibly through use of the SWA swivel adapter.
由于软管在管接头内扭曲而引起的机械应力导致磨损。可以通过使用SWA系列旋转适配器，从而避免在实际工作中产生的扭力。

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

Flat gaskets

扁平垫圈

In order to make the best choice of thread sealing element to use with a PMA connector or adapter in a specific application careful consideration must be made to all influencing factors and all components involved. It is not possible for PMA to make 100% clear cut recommendations about the correct sealing element to use for each connector and adapter because each application is different and PMA provides only part of the solution. Consideration of the mating parts is essential.

在特殊的应用中使用PMA管接头或适配器时，因每个应用环境不同，为了选择最佳的螺纹密封元件，必须仔细考虑到所有影响的因素及所涉及的组件，PMA不可能清楚地对每个管接头及适配器所适配的螺纹密封元件提供100%的建议，PMA仅提供部分的解决方案。要考虑到配对的部件，这是至关重要的。

Flat gaskets can provide a very effective seal between two flat surfaces. The total sealing area is the overlap between the connector flange, the mating surface and the gasket. Areas where one of these three elements are missing do not contribute to the sealing area. The system designer must ensure that the mating parts offer a large enough sealing area. If for example a connector does not sit in the middle of a through hole the sealing area will be reduced. Flat gaskets have the advantage that they can be effective even when the mating surface is slightly rough.

扁平垫圈可以在两个平面之间提供非常有效的密封。总密封面积为管接头法兰、配对表面及垫圈之间重叠的区域。缺少这三个元素任何一个，那就起不到相应的密封效果。系统设计者必须确保配对的部件提供足够大的密封面积，例如：一个管接头不位于通孔的中心，则密封区域将减少。扁平垫圈的优点在于，即使配对的表面稍微粗糙，它也能够提供有效的密封。



Flat gaskets 扁平垫圈

O-rings

O型圈

Successful use of an O-ring seal requires careful detail design of the mating threads. O-rings seal through elastic-plastic deformation of the cross-section of their material. The O-ring needs to be positioned precisely in a cavity which when the connector is fully installed has a volume 15-35% below the original volume of the O-ring. Many PMA metal thread connector have a recess at the end of the thread designed to position an O-ring. Due to the position of this recess it is unlikely the O-ring would be correctly compressed if the connectors is installed to a through hole and secured with a locknut. Metal parts and counterparts should be rounded and free from sharp edges.

The roughness of the mating surface should be checked to avoid O-ring damage during installation.

Twisting of the O-ring during installation should also be avoided.

有效使用O型密封圈需要仔细设计配合相应的螺纹，O型圈通过其材料横截面的弹性塑性变形密封。O型圈需要精确地定位在空腔中，当管接头完全安装时，其体积比O型圈的原始体积低15-35%。许多PMA金属螺纹管接头在设计时，就将O型圈定位在螺纹底端的凹槽内。由于该凹槽的位置，当管接头安装至通孔并用锁紧螺母固定，则O型圈未必能正确地被压缩。金属部件和对应部件应用圆形的，并且没有锋利的边缘。应检查配对的表面的粗糙度，以避免安装过程中造成O型圈损坏同时应避免在安装过程中扭曲O型圈。



O-rings O型圈

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

Thread sealing compound

螺纹密封剂

If a high degree of sealing is required in applications where the use of an O-ring or flat gasket are not possible due to the geometry of the mating parts, good sealing performance can be achieved by applying a thread locking and sealing compound to the thread itself.

如果由于配对的部件为几何形状而无法使用O型圈或扁平垫圈，且应用中需要更高的密封性能要求时，则可以将螺纹锁固和密封剂应用于螺纹本身，从而获得良好的密封性能。

Twisting of the O-ring during installation should also be avoided.

还应该避免在安装过程中扭曲O型圈。

Seals supplied with PMA connectors and adapters for use on male threads

PMA管接头和适配器提供的密封元件适配于外螺纹

- When only one type of seal is supplied with a PMA connector or adapter then this seal corresponds to the PMA recommendation. The use of another seal type may be technically inappropriate or insecure due to constructive details.
当PMA的管接头或适配器只供应一款密封元件时，则此密封元件符合PMA的推荐。基于结构上的细节，若使用另一款密封元件时，可能在技术上不适合或不安全。
- When both an O-ring and a flat gasket are delivered with a PMA connector or adapter it is intended that the customer should choose which element is more appropriate for his application depending upon the application, method of attachment and the mating parts.
当PMA管接头或适配器供应时包括O型圈和扁平垫圈，客户应根据应用环境、安装方式和相关的配对的部件去选择更加适合其应用的密封元件。
- **An O-ring and a flat gasket should never be used together, they will impede each other from functioning correctly.**
O型圈和扁平垫圈不能同时使用，因它们会互相妨碍彼此的功效。

General recommendations

一般建议

As a general rule if a PMA connector or adapter is to be installed to a through hole in a casing of some kind and secured with a lock nut on the other side, then a flat gasket offers the best chances of creating an effective seal. The flat gasket can be compressed around the hole between the casing and the connector flange.

一般来说，如果将PMA管接头或适配器安装在某种外壳的通孔中，并在另一侧用一个锁紧螺母固定，那么扁平垫圈可提供最佳的密封效果。扁平垫圈可压缩在外壳与管接头法兰之间的孔周围。

If a PMA connector or adapter is to be installed to a threaded hole, then if the contours of the mating thread entry are designed appropriately an O-ring can function very well and may be the better choice.

如果将PMA管接头或适配器安装在螺纹孔中，若螺纹接头设计匹配螺纹入口的轮廓，则O型圈可以发挥有效的密封效果，并且可能是比较好的选择。

If no suitable surfaces are available between which a flat gasket or O-ring could successfully be compressed then a thread sealing compound may be the only possible solution.

如果没有合适的表面让扁平垫圈或O型圈可以成功地被压缩，那么螺纹密封剂可能是唯一的解决方案。

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

The following PMA connectors and adapters are supplied with both an O-ring and a flat gasket:

以下的PMA管接头和适配器供货时包含O型圈和扁平垫圈：

Male metal thread connectors 公制金属螺纹管接头	Thread 螺纹 (M)	Product series 产品系列: NKNH-M, NKAH-M, NKBH-M N/MVNV-M, N/MVWV-M, N/MVBV-M, N/MVAV-M
Metal thread swivel connectors 金属螺纹旋转管接头	Thread 螺纹 (M, PG)	Product series 产品系列: NSNV-M/P, NSBV-M/P, NSWV-M
Metal thread adapters 金属螺纹适配器	Thread 螺纹 (M, PG)	Product series 产品系列: SWA-M/P, SCA-M/P, MAVI-M/P

For these articles the most suitable sealing element should be selected according to the application conditions

对于以上的产品，应根据应用条件选择最适合的密封元件

The following PMA adapters are supplied with an O-ring only

以下PMA适配器只提供O型圈

Metal thread adapters 金属螺纹适配器	Thread 螺纹 (M)	Product series 产品系列: SCAK-M, MAVIK-M
----------------------------------	------------------	---

The following PMA connectors and adapters are supplied with a flat gasket only:

以下的PMA管接头和适配器只供应扁平垫圈：

Male, metal thread connectors 金属外螺纹管接头	Thread 螺纹 (PG, NPT)	Product series 产品系列: N/MVNV-P/N, N/MVWV-P, N/MVBV-P, N/MVAV-P
Male, metal swivel connectors 金属外螺纹，旋转管接头	Thread 螺纹 (NPT)	Product series 产品系列: NSNV-N, NSBV-N
Male, plastic thread connectors 塑料外螺纹管接头	Thread 螺纹 (M) (M, PG, NPT)	Product series 产品系列: B/SKNH-M, B/SKAH-M, B/SKBH-M B/SVNV-P/M/N, B/SVAV-P/M/N, B/SVWV-P/M/N

None of the articles above have a recess at the end of the thread to precisely define the position of an O-ring. They are supplied with a flat gasket only.

上面的任何一个产品都没有在螺纹的底端有一个凹槽来精确地定位O型环的位置。他们只提供扁平垫圈。

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

The following PMA strain relief connectors are delivered with an O-ring only. If the geometry of the mating parts does not allow correct compression of the O-ring a thread locking and sealing compound may be necessary to achieve a high level of sealing performance.

以下的PMA消除应力管接头只供应O型圈。如果适配部位的几何形状使O型圈不能被正确压缩，则可能需要应用螺纹锁定和密封剂，从而达到更高的密封性能。


Strain relief connectors 消除应力管接头	Thread 螺纹 (M, PG)	Product series 产品系列: NVNZ-M/P, NVNZ-P/P, (Pflitsch system) NVNZ-M, NVNZ-P (Jacob system)
-------------------------------------	----------------------	--

The O-rings supplied with PMA strain relief connectors are pre-installed to the termination thread by Pflitsch.

PMA follows the recommendation of the cable gland manufacturer.

PMA 消除应力管接头提供的O型圈，来自Pflitsch公司。O型圈是预先安装在螺纹底端上。

PMA遵循电缆索头制造商的建议。



Metric NVNZ-MxxxS / Px; NVNZ-MxxxS / Px - L (Pflitsch UNI Dicht 系列)

Thread size 螺纹尺寸	ID mm	d mm	O-ring ID x d (mm) O型圈内径 x 厚度(毫米)
M12 x 1.5	10.5	1.5	10.5 x 1.5
M16 x 1.5	13.0	1.5	13.0 x 1.5
M20 x 1.5	17.0	1.5	17.0 x 1.5
M25 x 1.5	22.0	1.5	22.0 x 1.5
M32 x 1.5	28.0	2.0	28.0 x 2.0
M40 x 1.5	38.0	2.0	38.0 x 2.0
M50 x 1.5	45.0	2.0	45.0 x 2.0
M63 x 1.5	58.0	2.0	58.0 x 2.0

PG NVNZ-PxxxS / Px (Pflitsch UNI Dicht 系列)

Thread size 螺纹尺寸	ID mm	d mm	O-ring ID x d (mm) O型圈内径 x 厚度(毫米)
Pg7	10.5	1.5	10.5 x 1.5
Pg9	12.0	1.5	12.0 x 1.5
Pg11	14.0	1.6	14.0 x 1.6
Pg13.5	17.0	1.5	17.0 x 1.5
Pg16	20.0	1.5	20.0 x 1.5
Pg21	26.0	1.5	26.0 x 1.5
Pg29	33.0	2.0	33.0 x 2.0
Pg36	42.0	2.0	42.0 x 2.0
Pg42	50.0	2.0	50.0 x 2.0
Pg48	55.0	2.0	55.0 x 2.0

Metric NVNZ-MxxxS / PBGx (Pflitsch blueglobe 系列)

Thread size 螺纹尺寸	ID mm	d mm	O-ring ID x d (mm) O型圈内径 x 厚度(毫米)
M12 x 1.5	11.0	1.5	11.0 x 1.5
M16 x 1.5	15.0	1.5	15.0 x 1.5
M20 x 1.5	19.0	1.5	19.0 x 1.5
M25 x 1.5	24.0	1.5	24.0 x 1.5
M32 x 1.5	30.0	1.5	30.0 x 1.5
M40 x 1.5	38.0	1.5	38.0 x 1.5
M50 x 1.5	48.0	2.0	48.0 x 2.0
M63 x 1.5	61.0	2.0	61.0 x 2.0

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

The following PMA strain relief connectors are delivered with an O-ring only. If the geometry of the mating parts does not allow correct compression of the O-ring a thread locking and sealing compound may be necessary to achieve a high level of sealing performance.

以下的PMA消除应力管接头只供应O型圈。如果适配部位的几何形状使O型圈不能被正确压缩，则可能需要应用螺纹锁定和密封剂，从而达到更高的密封性能。

The O-rings supplied with PMA strain relief connectors are pre-installed to the termination thread by Jacob. PMA follows the recommendation of the cable gland manufacturer.

PMA消除应力管接头提供的O型圈，来自Jacob公司。O型圈是预先安装在螺纹底端上。PMA遵循电缆索头制造商的建议。



Metric

NVNZ-M (Jacob PERFECT 系列)

Thread size 螺纹尺寸	ID mm	d mm	O-ring ID x d (mm) O型圈内径 x 厚度 (毫米)
M12 x 1.5	9	1.5	9.0 x 1.5
M16 x 1.5	13	1.5	13.0 x 1.5
M20 x 1.5	18	1.5	18.0 x 1.5
M25 x 1.5	21	2.0	21.0 x 2.0
M32 x 1.5	29	2.5	29.0 x 2.5
M40 x 1.5	37	2.0	37.0 x 2.0
M50 x 1.5	47	2.5	47.0 x 2.5
M63 x 1.5	60	3.0	60.0 x 3.0

PG

NVNZ-P (Jacob PERFECT 系列)

Thread size 螺纹尺寸	ID mm	d mm	O-ring ID x d (mm) O型圈内径 x 厚度 (毫米)
Pg7	10.0	1.5	10.0 x 1.5
Pg9	13.0	2.0	13.0 x 2.0
Pg11	16.0	2.0	16.0 x 2.0
Pg13.5	18.0	2.0	18.0 x 2.0
Pg16	20.0	2.0	20.0 x 2.0
Pg21	24.0	2.0	24.0 x 2.0
Pg29	33.0	2.0	33.0 x 2.0
Pg36	42.0	2.5	42.0 x 2.5
Pg42	48.0	2.5	48.0 x 2.5
Pg48	54.0	3.0	54.0 x 3.0

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

NPT Threads


NPT 螺纹

In North America NPT threads are widely used. To serve this market PMA offers a number of connector types with this type of threads. Both metal thread and polyamide thread types.

While Metric (IEC EN60423) and PG (DIN40430) thread types are cylindrical in form with parallel sides, NPT threads are tapered in a conical form.


在北美NPT螺纹被广泛使用。为了服务于这个市场，PMA提供了许多此系列螺纹的管接头，金属螺纹和聚酰胺螺纹两种类型。公制（IEC EN60423）和PG（DIN40430）螺纹类型为平行的圆柱形，但NPT螺纹呈锥形。

1. NPT Tapered Pipe Threads



NPT (National Pipe Tapered) is made to specifications outlined in ANSI B1.2.

4. ISO 228/1 Parallel Pipe Threads



For parallel threads high tightening torques are only achieved when the end of the thread is reached. Usually two flanges meet and sealing element can be placed between them.

对于平行螺纹，只有在达到螺纹底端部时才能实现高拧紧扭矩。通常是两个法兰连接，密封元件放置在它们之间。

For tapered or conical threads such as NPT types the torque increases as the mating threads are turned relative to one another. These types of thread are not ideally suited to flange sealing techniques. They were conceived as the name suggests (National Pipe Thread) for sealing of metal pipes without a flange.

对于诸如NPT系列的锥形或圆锥形螺纹，当匹配螺纹相对转动时，扭矩增大。这些系列的螺纹不适合法兰密封技术。他们顾名思义认为（国家管螺纹）密封金属管连接时不需要法兰密封。

If a conical thread is used for flange sealing there is a danger that...

....either a very high tightening torque will be reached before the two flange surfaces meet,

....or the flange surfaces meet at a very low torque and the threads are still loose.

如果锥形螺纹用于法兰密封，则存在以下危险：

....在两个法兰面连接之前，要么达到很高的拧紧力矩，

....要么法兰表面以非常低的扭矩相交，螺纹仍然松动。

Sealing elements for use with the threads of PMA connectors and adapters: O-rings, flat gaskets, thread sealing compound. 适用于PMA管接头和适配器的密封元件：O型圈、扁平垫圈、螺纹密封剂

PMA female thread connectors and adapters:

PMA内螺纹管接头及适配器：

The following PMA connectors and adapters are supplied with an O-ring which sits in a recess at the end of the female thread:

以下PMA管接头和适配器提供O型圈，它位于内螺纹底端的凹槽中：

Female PA thread connectors / adapters 聚酰胺内螺纹管接头 / 适配器	Thread 螺纹 (UNEF, M)	Product series 产品系列: BKIHG-U, BVIVG-U, BVIVG-M, BVIDG-U
Female metal thread connectors / adapters 金属内螺纹管接头 / 适配器	Thread 螺纹 (UNEF, M)	Product series 产品系列: NVIVG-U, NVIVG-M, NSHV-U, NVIZG-U

For female thread connectors it is particularly important to consider the contours of the mating male thread. If the connector is installed to a male thread connector, the connector itself may have a sealing element. If the O-ring at the back of one of the connectors mentioned above is to be compressed correctly the contour at the end of the male thread must be appropriate and the thread length must be considered. If the connector thread is shorter than the PMA female thread the O-ring will not be reached.

对于内螺纹管接头，特别重要的是考虑配合外螺纹的轮廓。如果管接头安装到外螺纹连接器上，连接器可能本身具有密封元件。如果上述配件之一的O型圈正确被压缩，则外螺纹端部的轮廓必须匹配，并且必须考虑螺纹长度。如果连接器螺纹短于PMA内螺纹，则O型圈不能被压缩。

It is often easier to find a connector which is compatible with the thread size of a circular connector than it is to find one which seals correctly.

找一个与圆形连接器螺纹尺寸相匹配的管接头比找到一个正确密封的管接头更容易。

The PMA series BKIHG - U, BVIVG - U, BVIDG - U were specifically designed for compatibility with MIL - DTL - 5015H circular connectors.

The thread length ensures correct compression of the O-ring at the end of the PMA thread.

PMA系列BKIHG - U, BVIVG - U, BVIDG - U专为兼容 MIL-DTL - 5015H 圆形连接器而设计。

螺纹长度可确保在PMA螺纹底端的O型圈受到压缩，达到密封效果。

BVIDA-U, BVIRA-U were designed for compatibility with AMP connectors of specific series.

BVIDA-U, BVIRA-U特别设计适合兼容AMP某一系列的连接器。

BVIDB - U, BVIRB - U and BVIRS - U were designed for compatibility with Souriau (formerly Burndy) and / or ITT Cannon connectors.

BVIDB - U, BVIRB - U和BVIRS-U特别设计适合兼容某系列的苏里奥（原先的奔迪）和/或 ITT Cannon的连接器。

If the thread size and type of a PMA connector and a circular connector are compatible but a sealing element cannot be used for one reason or another.

Then a thread sealing compound can be used to seal the junction between the two threads.

如果PMA管接头和圆形连接器的螺纹尺寸和类型是兼容的，但密封元件由于某种原因不能使用，则可使用螺纹密封剂来密封两个螺纹之间的连接部分。

Adhesives and Sealing Agents for threads on PMA Fittings & Accessories

粘合剂和密封剂与PMA管接头 & 配件的使用

Based on tests performed in house with various materials at different temperatures and experience gained from real applications ABB PMA Cable Protection can recommend the following adhesives for good long-term thread locking and sealing performance.

根据不同的材料在不同温度下进行内部测试以及从实际应用中获得的经验，ABB PMA电缆保护系统推荐以下能提供良好的长期锁固和密封性能的螺纹粘合剂。

Which product is most suitable for your particular application depends upon a number of different factors, e.g. temperatures, materials, handling issues (single component, dual component adhesive), required conductivity etc.

哪种产品最适合您的特定应用取决于一系列的因素，如：温度、材料、处理问题（单组分、双组分粘合剂），所需的导电性等。

Care should always be taken when using adhesives to ensure that surfaces are clean and prepared correctly before application. Adhesive properties can be improved using surface cleaning agents and primers.

使用粘合剂时，应始终采取正确的处理，确保使用前表面清洁。使用表面清洁剂和底漆，能提高粘合性能。

Please consult the appropriate manufacturer's data sheet before using one of these adhesives to ensure the suitability for a particular application and for detailed application recommendations.

在使用这些粘合剂之前，请参阅制造商的数据表，以确保其适合特定应用以及详细的应用建议。

Adhesives and Sealing Agents for threads on PMA Fittings & Accessories

粘合剂和密封胶与PMA管接头 & 配件的使用

	Loctite 262 乐泰 262	Loctite 542 乐泰 542	Loctite 480 乐泰 480	3M DP 490 3M DP 490	Loctite 9483 50ml 2k Epoxy 乐泰 9483 50ml 2k 环氧树脂	Panacol Elecolit 325 聚酰胺胶 325
Electrical Conductivity 导电性	NO 否	NO 否	NO 否	NO 否	NO 否	Yes - For use with EX - System & EMC System 是 - 适用于Ex系统和 EMC系统
Locking & Sealing 锁固 & 密封	Yes 是	Only Sealing 仅密封	Only Locking 仅锁固	Yes 是	Yes 是	No information available 无可用信息
Temperature Range 温度范围	-55°C to +150°C -55°C 至+150°C	-55°C to +150°C -55°C 至+150°C	max. temp. approx. 100°C 最高温度100°C	-55°C to +120°C -55°C 至+120°C	-55°C to +150°C -55°C 至+150°C	-40°C to +150°C -40°C 至+150°C
Metal Threads Connection* 金属螺纹连接	Recommended 推荐	Recommended up to 120°C 建议120°C以下	Recommended up to 100°C 建议100°C以下	Recommended up to 120°C 建议120°C以下	Recommended 推荐	No information available 无可用信息
Polyamide Threads Connection 聚酰胺螺纹连接	Not Recommended 不推荐	Not Recommended 不推荐	Recommended up to 70°C 建议70°C以下	Recommended 推荐	Recommended 推荐	No information available 无可用信息
Mixed Threads Connection 混合螺纹连接	Recommended up to 70°C 建议70°C以下	Recommended up to 70°C 建议70°C以下	Recommended up to 70°C 建议70°C以下	Recommended up to 100°C 建议100°C以下	Recommended up to 120°C 建议120°C以下	No information available 无可用信息
Re - Opening (all thread material types) 重新打开 (所有螺纹材料类型)	Yes 是	Yes 是	Yes 是	Solvent & / or high temperature may be required 可能需要溶剂 & / 或者高温	Solvent & / or high temperature may be required 可能需要溶剂 & / 或者高温	No information available 无可用信息
Single or Two Component Adhesive 单组分或双组分粘合剂	Single 单组分	Single 单组分	Single 单组分	Two Component 双组分	Two Component 双组分	Two Component 双组分

We reserve the right to make technical changes or modify the contents of this document without prior notice.

ABB PMA Cable Protection does not accept any responsibility whatsoever for potential errors or possible lack of information in this document.

我们保留对本文件内容进行技术更改或修改的权利，恕不另行通知。ABB PMA电缆保护不对本文件中的潜在错误或可能存在信息欠缺承担任何责任。

Please note, the information in this document is for general information only; it is not and shall not be used to create an express or implied warranty of performance or life expectancy.

请注意，本文档中的信息仅供一般参考；它不是也不应被用来对性能或预期寿命做出明示或暗示的保证。

Applications engineering information

应用工程信息

Fill factor, relevant guidelines

填充率相关指导

Fill factor max.70%
最大填充率 70%

The question of conduit capacity or fill factor arises in the use of cable protection systems. This describes the extent to which a conduit can or should be filled with cables and/or conductors based on the available cross-sectional area.

在电缆保护系统应用中，会出现软管填充容量的问题，即软管能充电缆或导线的程度。

In all cases, **PMA** recommends that a conduit **capacity of 70%** not be exceeded. (Application-specific procedures and standards must also be considered.)


在所有情况，**PMA** 建议软管容量不要超过 70%（详细应用的情况和标准也必须加以考虑）。

This ensures that operation is not unnecessarily impaired by increased friction between the individual conductors in dynamically moving systems. In addition, subsequent installation of additional conductors and/or cables also possible if necessary.

这保证在动态运动系统中，各导线不断增强的摩擦力不会产生不必要的损坏，另外，如果需要的话，也可以再次安装增加的导线或电缆。

Wiring installation: fixation

电缆安装：紧固



PMA recommends that cable protection systems be fastened with a spacing of **300 to 500 mm** between supports. This spacing can be varied depending on the application and location. This recommendation applies for all available dimensions. For larger diameters, the increased load due to the cables and conductors in the conduit is accounted for by adherence to the support spacing. **PMA** supplies suitable system supports for various strength requirements and applications.

PMA 推荐需对电缆保护系统进行紧固，支架点要求有 **300 到 500mm** 的空间间隔。这个空间可以根据实际应用和安装位置进行调整，可用于各种外形尺寸。对于大口径软管，由于管内电缆和导线而增加的负载将影响支架点的空间间隔，**PMA** 对于不同的强度要求和应用提供相应的支撑系统。

European standard EN 50343:2003-5.15 “Railway applications - Rolling stock - Rules for installation of cabling” specifies the following spacing between supports for fastening conductors:

欧洲标准 EN 50343:2003-5.15 “铁路应用 - 全部车辆 - 电缆安装规则” 确定如下紧固导线支架点间隔：

Horizontal wiring: 300mm
Vertical wiring: 500mm

水平线缆 300mm
垂直线缆 500mm

(Application specific guidelines and standards have to be additionally considered.)

(特别的应用指导和标准必须额外考虑)

Storage recommendation for polyamide products

聚酰胺产品贮存建议

Polyamide is widely and successfully used for products in the electrical and electronics industries. Thanks to its excellent mechanical and physical properties over a wide range of application temperatures and its very good weather resistance, polyamide can be used to make products for interior and external use that meet the most stringent of demands.

As a hygroscopic material, polyamide has the ability to absorb moisture in molecular form into the plastic matrix. As the moisture content goes up, product properties may change slightly, displaying increased toughness and lower rigidity for example.

The following table shows how the moisture content of polyamides comes into balance with the ambient air in a normal climate of 50% relative humidity and 23°C:

聚酰胺广泛及成功地应用于电气和电子行业。由于其在广泛的应用温度范围内,具有良好的耐候性,以及优异的机械和物理性能,因此聚酰胺可用于制造高技术要求的室内和室外产品。

聚酰胺作为一种吸湿材料,具有将分子形式的水分吸收到塑料基体中的能力。随着含水量的增加,产品性能可能略有变化,例如会体现出柔韧性增加和降低硬度。

下表显示了在50%相对湿度和23°C的一般气候下,聚酰胺的含水量如何与环境空气取得平衡:

Material 材质	In air (23° C/50% r.h.) 空气中 (23° C/50% r.h.)
PA6	2 ... 3% by weight
PA12	0.8 ... 1.2% by weight

To maintain a balanced moisture content, PMA recommends storing products under the following conditions:
为了保持水分平衡, PMA建议在以下条件下储存产品:

Storage temperature 储存温度	Processing temperature 加工温度	Rel. humidity 相对湿度
18°C ... 30°C	>18°C	>30%

At lower processing temperatures and in particular when subjected to unnatural drying, corrugated pipes display increased flexural rigidity.

In the very dry winter months the moisture balance may go down slightly as the material releases moisture to the environment (owing to lower rel. humidity).

Compared to natural outdoor conditions* at around 0°C (40 to 80% rh), the humidity in heated rooms may drop by half to below 20% rh if no humidification is present. (Even extremely dry regions such as the Sahara Desert record average humidity of 20% to 60% rh.)

If products from an outside environment are brought into a heated processing area, the change in climate may suddenly cause temporary demoisturization around the edges. After one or two days in the processing area a natural balance will be restored.

Most PMA products have been modified to make them immune to climate changes of this kind.

Observing this storage recommendation ensures optimum processability and material properties.

* Central European climate

在较低的加工温度下,尤其是在非自然干燥条件下,波纹管展示出增加的抗弯刚度。

在非常干燥的冬季,当材料向环境释放水分时(由于较低的相对湿度),水分平衡可能会略微下降。

与0°C (40%至80%rh)的自然室外条件*相比,如果不存在加湿,在加热室内的湿度可能会下降一半至低于20%rh。(即使是非常干燥的地区,如撒哈拉沙漠,记录的平均湿度为20%至60%rh。)

如果来自外部环境的产品被带到加热的加工区,气候的变化可能会突然在边缘周围造成暂时的水份失去,但在加工区域停留一两天后,将恢复平衡。

大多数PMA产品都经过了改良,以便适应相应的气候变化。

遵守此存储建议可确保最佳的加工性和材料性能。

* 中欧气候区

Chemical resistance

抗化学性能

Resistance against	防护	Chemical Formula 化学分子式	PA6	PA12	PP	TPU	PFA
			Polyamide 6 PA66 Polyamide 66	Polypropylene PA11 Polyamide 11	Polypropylene PE Polyethylene	Thermoplastic Polyurethane elastomer	Perfluoroalkoxy- copolymer PVDF Polyethylene fluoride
Acetic acid (10%)	醋酸 (10%)	C ₂ H ₄ O ₂	●	●●	●●●	○	●●●
Acetone	丙酮	C ₃ H ₆ O	●●●	●●●	●●●	○	●●●
Ammonia (30%)	氨水 (30%)	NH ₃	●●●	●●●	●●●	○	●●●
Benzine	汽油	-	●●●	●●●	●●●	●	●●●
Brake fluid	制动液	-	●●●	●●●	●●●	○	●●●
Caustic soda	苛性钠	NaOH	●●●	●●●	●●●	●	●●●
Ethyl alcohol (40%)	乙醇 (40%)	C ₂ H ₆ O	●●●	●●●	●●●	●	●●●
Glycol	烯糖	C ₂ H ₆ O ₂	●●●	●●●	●●●	○	●●●
Hydrochloric acid (10%)	盐酸 (10%)	HCL	○	●	●●●	○	●●●
Methanol	甲醇	CH ₄ O	●●	●●●	●●●	●	●●●
Methyl ethyl ketone	丁酮	C ₄ H ₈ O	●●●	●●●	●●●	○	●●●
Nitric acid (10%)	硝酸 (10%)	HNO ₃	○	○	●●	○	●●●
Ozone	臭氧	O ₃	●●	●●	●●	●	●●●
Paint thinner	涂料稀释剂	-	●●●	●●●	●	○	●●●
Perchloroethylene	全氯乙烯	C ₂ Cl ₄	●●	●●	●●	○	●●●
Paraffin	石蜡	-	●●●	●●●	●	○	●●●
Phosphoric acid (10%)	磷酸 (10%)	H ₃ PO ₄	●	●●	●●●	○	●●●
Sea water	海水	-	●●●	●●●	●●●	●●	●●●
Soap solution	肥皂水	-	●●●	●●●	●●●	●●	●●●
Sodium chloride	氯化钠	NaCl	●●●	●●●	●●●	●●●	●●●
Sulphuric acid (10%)	硫酸 (10%)	H ₂ SO ₄	●	●●	●●●	○	●●●
Toluene	甲苯	C ₇ H ₈	●●●	●●●	●	○	●●●
Trichlorethylene	三氯乙烯	C ₂ HCl ₃	●	●●	○	○	●●●
Turpentine	松节油	-	●●●	●●●	○	○	●●●
Urine	稀释尿液	-	●●●	●●●	●●●	●●●	●●●
Resistance against Oils and Fats	防护油和脂	-					
Cutting oils*	切削液	-	●●●	●●●	●●	●	●●●
Diesel oil	柴油	-	●●●	●●●	●●	●●	●●●
ASTM Oil Nr.3.	ASTM No.3 油	-	●●●	●●●	●●	●	●●●
Fuel oil	燃油	-	●●●	●●●	●●	●	●●●
Hydraulic oils*	液压油	-	●●●	●●●	●●	●	●●●
Mineral oils	矿物油	-	●●●	●●●	●●	●●●	●●●
Spark-erosion liquids	电火花腐蚀液	-	●●●	●●●	●●	●	●●●
Skydrol	特种液压工作油	-	●	●●	●●	○	●●●
Transformer oils*	变压器油	-	●●●	●●●	●●	●	●●●

* Synthetic additives can affect the oil resistance of plastics. Please contact PMA for further information

- Excellent resistance / suitable for permanent contact
- Resistant/suitable for occasional contact
- Relatively resistant / suitable for short-term contact
- Not recommended

* 合成添加剂会影响塑料的防油性能，请联系PMA咨询进一步信息。

- 有极好的抵抗力/适合永久接触。
- 有良好的抵抗力/适用非经常接触。
- 有相当的抵抗力/适用短时间接触。
- 不推荐。

Important:

The chemical resistance of plastic products is also dependant on factors such as temperature, amount of time exposed to chemicals (e.g.occasional contact or immersed) as well as the concentration of the specific chemicals.

The stated chemical resistances are valid for a temperature of 20°C. The chemical resistance table above serves only as a guide for the use of polyamide products in conjunction with the listed chemicals. Each specific application should be controlled for suitability by the end-user. A more detailed table can be found on the PMA Homepage under www.pma.ch.

注意:

塑料产品的抗化学性能同样取决于其它因素，如：温度、暴露在化学物质中的时间（非经常接触或浸没等情况）、浓度等。

上述抗化学性能在20°C温度环境下有效。

上述抗化学性能表仅是对聚酰胺产品与所列化学物质的简要指南。为了正确使用，终端用户应要控制每个特定应用情况的适用性。

更多详细表格可查阅PMA网站www.pma.ch.



Important information

The specifications and instructions for our customers in this document reflect the product engineering level at the time of manufacturing. **PMA** accepts no liability for damages resulting from unprofessional installation or application or misuse for a purpose. This disclaimer also includes damages to third parties. It is the customer's responsibility to check the delivered products and immediately notify **PMA** of detected faults. It is also the customer's responsibility to test the delivered product on its applicability for the intended purpose, **PMA** will accept liability or responsibility for their products if a product or a **PMA** system is combined or used together with third-party products, i.e. products from other companies than **PMA**. Jurisdiction in all legal disputes concerning product liability have the courts of the canton of Zurich / Switzerland. Swiss law applies.

To guarantee punctual deliveries please check availability of products before ordering.

The text, pictures, drawings and application photos which are published in this document may not, in part, or totally, be copied or used by any third party in any form or way. Especially the downloading of text, pictures, drawings, and application photos onto Online Services is strictly forbidden, irrespective of if they are edited for this purpose or not. At all times **PMA** reserves the right to make all legal steps necessary.

For more information go to:
www.pma.ch

To order / download our catalogues
Please refer to www.pma.ch

重要信息

本档中的技术规格和对于客户的产品使用说明，反映了制造时的产品工艺水平。**PMA**对于非专业的安装使用以及选型错误造成的损害不承担责任，本声明也包括对第三方造成的损害。客户负责检查运输到来的产品，以及立即通知**PMA**检查到的问题。客户也负责在应用产品时对它们进行测试。对于将**PMA**产品或系统与第三方产品例如非**PMA**产品结合时使用情况，**PMA**不承担责任。关于产品责任的所有法律争议的权限由瑞士苏黎世法院依据瑞士法律仲裁。

为保证准确的产品运输时间，请在订购之前检查产品的库存量。

在本书中出现的文字、图案、表格以及照片都不能部分或全部的复制，更不能被第三方用于其它方面，特别严禁从网站上拷贝文字、图案、表格和照片，不管这些资料是否有用。在任何情况下，**PMA**有权在必要的时候通过法律手段来解决问题。

更多信息请访问
www.pma.ch

如要下载样本请访问
www.pma.ch

